

304 / 304L Stainless

Technical Datasheet



Service. Quality. Value.

Austenitic Stainless Steel

Typical Applications

- Pharmaceutical processing equipment
- Chemical processing equipment
- Architectural applications
- Sinks & splash backs
- Tubing
- Springs, nuts, bolts & screws

Product Description

Type 304 stainless steel is an austenitic alloy containing 18% chrome and 8% nickel. The alloy has a lower carbon content which minimizes chromium carbide precipitation due to welding and its susceptibility to intergranular corrosion. Weldability and forming properties of Type 304 are excellent whilst machinability is reasonable. The alloy also benefits from very good drawability. A combination of low yield strength and high elongation allows for the forming of complex shapes, although it should be noted that the material hardens rapidly. Type 304L is the low carbon version of 304, does not require post-weld annealing and so is extensively used in heavy gauge components (over about 6mm).

Key features

- Austenitic stainless steel
- Contains 18% chrome and 8% nickel
- Excellent welding and forming properties
- Machinability is reasonable

Machinability

Reasonable machinability.

Weldability

By common welding techniques.

Availability

Round Bar, plate, sheet, wire tube.

Corrosion resistance

Excellent resistance to a wide range of atmospheric, chemical, textile, petroleum and food industry exposures.

Chemical Composition (weight %)

	C	Cr	Mn	Si	P	S	Ni	Fe	
min		17.50					8.00		
max	0.07	19.50	2.00	1.00	0.05	0.02	10.50	Bal	

Mechanical Properties

Tensile strength	500 - 700	MPa
Proof Stress	210 min	MPa
Elongation A5	45 min	%

Physical Properties

Density	8.00	kg/m ³
Melting Point	1450	°C
Modulus of Elasticity	193	GPa
Electrical Resistivity	0.072	x10 ⁻⁶ Ω.m
Thermal Conductivity	16.2	W/m.K
Thermal Expansion	17.2	x10 ⁻⁶ /K

UK Service Centres:

Smiths Belfast 02895 908 897
Smiths Biggleswade 01767 604 704
Smiths Birmingham 0121 728 4940
Smiths Bristol 0117 971 2800
Smiths Chelmsford 01245 466 664
Smiths Gateshead 0191 469 5428
Smiths Horsham 01403 261 981

Smiths Leeds 0113 307 5167
Smiths Manchester 0161 794 8650
Smiths Norwich 01603 789 878
Smiths Nottingham 0115 925 4801
Smiths Redruth 01209 315 512
Smiths Verwood 01202 824 347
Main Office 0845 527 3331

Quality & Testing:



www.smithmetal.com info@smithmetal.com

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.