

UNS S32750 / 1.4410 / F53

Technical Datasheet



Service. Quality. Value.

Duplex Stainless Steel

Product Description

Material to UNS S32760 (and the other specifications listed below) is described as a super duplex stainless steel with a microstructure of 50:50 austenite and ferrite. The steel combines high mechanical strength (typically up to 570 MPa yield strength) and good ductility with outstanding corrosion resistance in marine environments. The alloy is supplied with a PREN (Pitting Resistance Equivalent) at ≥ 40.0 which guarantees high resistance to pitting corrosion. In addition, the steel offers high resistance to crevice corrosion and stress corrosion cracking. Ambient and sub-zero (down to minus 50°C) notch ductility is good. These attributes mean that this super duplex steel can be used successfully as an alternative to 300 series stainless steel (such as type 316), standard 22% Cr duplex steel (such as UNS S31803 / 1.4462 with PREN 33-34) and precipitation hardening stainless steels (typically 17/4PH).

Availability

Bar, forgings, sheet, plate, pipe, tube, closed die forgings, flanges and welding consumables.

Machinability / Welding

The machining and welding of this grade of duplex stainless steel presents no particular problems. Guidance notes are available upon request.

Typical Applications

Pumps, valves, chokes, Xmas trees, pipework / flanges, bolting, connectors & manifolds. In oil and gas industry.

Related Specifications

- UNS S32750 in various ASTM product form specifications
- EN 10088-3 1.4410 (Grade X2CrNiMoN25-7-4)
- NORSOK MDS D51 to D55 D57 & D58
- ASTM A182 F53
- NACE MR01-75 (latest revision) / ISO 15156

Chemical Composition (weight %)

Weight (%)	C	Mn	Si	S	P	Cr	Ni	Mo	N	*PreN
Min						24.0	6.0	3.0	0.24	40
Max	0.03	2.00	1.00	0.015	0.035	26.0	8.0	4.5	0.35	

* PREN = Cr % + 3.3Mo% + 16N%

Minimum Mechanical Properties at Room Temperature

(EN10088-3 1.4410 max diameter 160mm - Solution Treated)

Ultimate Tensile Strength	730 – 930 MPa	(106 – 135 ksi)
0.2% Proof Strength	530 MPa	(77 ksi)
Elongation	25 %	
Hardness (Max)	290 HB	
Impact	100 J	(74 ft.lb)

Typical Properties

Density	7.8	kg/dm ³
Specific Thermal Capacity at 20°C	500	J.Kg ⁻¹ .K ⁻¹
Mean Coefficient of Thermal Expansion at 20 - 100°C	13.0	x 10 ⁻⁶ K ⁻¹
Thermal Conductivity at 20°C	15	W.m ⁻¹ .K ⁻¹
Electrical Resistivity at 20°C	0.80	Ω.mm ² .m ⁻¹
Modulus of Elasticity at 20°C	200	GPa
Magnetisable	Yes	

UK Service Centres:

Smiths Belfast **02895 908 897**
Smiths Biggleswade **01767 604 704**
Smiths Birmingham **0121 728 4940**
Smiths Bristol **0117 971 2800**
Smiths Chelmsford **01245 466 664**
Smiths Gateshead **0191 469 5428**
Smiths Horsham **01403 261 981**

Smiths Leeds **0113 307 5167**
Smiths Manchester **0161 794 8650**
Smiths Norwich **01603 789 878**
Smiths Nottingham **0115 925 4801**
Smiths Redruth **01209 315 512**
Smiths Verwood **01202 824 347**
Main Office **0845 527 3331**

Quality & Testing:



www.smithmetal.com info@smithmetal.com

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.